

Data Sheet

Material:	Nylon6CF (PA6CF)		
Print temperature:	240-260℃		
Density:	1.2g±0.05g/cm ³		
Melt flow index:	8 (190℃/2.16kg)		
Printing speed:	40-100(mm/s)		
Tensile strength:	≥118Mpa		
Flexural modulus:	5160Mpa		
Elongation at break:	5%		
Distortion Temp.	160℃		
Cooling Fan	Turn off		
Net weight:	1kg 400m		
Bed temperature:	100-120℃		

Roll Size

